TECHNICAL DATA

Version 1

AT326 Double Sided Flooring Tape

General Description

Technical Details Typical Values

Release liner weight

Breaking Load

Adhesion to Steel

RoHS compliant

Service Temperature

Storage Temperature

Application Temperature

Faced Side

Unfaced Side

Elongation

Release liner thickness

Tape thickness (Excluding liner)

A green polythene LDPE film with the faced side coated with a permanent non-solvent synthetic rubber resin adhesive and the unfaced side coated with a removable acrylic adhesive, interleaved with a siliconised paper release liner.

0.15mm

80gsm

70 µm

20 N/cm

7.2 N/cm

2.5 N/cm

-10°C to +50°C

0°C to +40°C

+12°C to +25°C

Yes

210%

- Clean peel from unfaced side
- Conformable to awkward shapes



NOTE

Except where indicated otherwise, the figures stated are typical values and should not be regarded as MAXIMUM or MINIMUM values for specification purposes. The Company reserves the right to improve products and any change in specification will result in a re-issue of the relevant 'Technical Data Sheet'. Customers should satisfy themselves that the tape is suitable for their requirements whether after such modifications or otherwise. Please check that you have the latest issue of the 'Technical Data Sheet'. All slitting and length tolerances are to British Standards. Before use the customer is advised to consult the Health & Safety Data Sheet produced by the company for this product, which is available on request.

STORAGE

Tapes stored below the minimum recommended temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.



AFERA

Association des Fabricants Européens de Rubans Auto-Adhésifs.

Adding more to adhesive tape

Registered in England No. 929843 Vat No. 115-6143-00 Advance Tapes International Limited Westmoreland Avenue Thurmaston Leicester LE4 8PH England Tel. +44 (0)116 251 0191 Fax. +44 (0)116 265 2046 contact@advancetapes.com

www.advancetapes.com