

TECHNICAL DATA

Version 5

AT528 50 Micron Copper Foil Shielding Tape

General Description

50 micron copper foil coated with an electrically conductive thermosetting solvent based acrylic adhesive supplied on a removable silicone liner.

- Conductive acrylic adhesive
- Good high and low temperature resistance
- Can be easily soldered
- Easy unwind

Specifications

Tested in accordance with ASTM D-1000 latest issue,
BS EN 60454 - Part 2 test methods (Formerly VDE 0340, BS 3924.)
Tested and meets military specification MIL – T – 47012
Construction is tested in-house and conforms to the Flame Retardant requirement part only of UL510

Technical Details

Technical details	BS value	ASTM value
Foil thickness:	0.050mm	2.0 mil
Adhesive thickness:	0.025mm	1.0 mil
Total thickness	0.075mm	3.0 mil
Adhesion to steel	4.5 N/cm	41 oz/inch
Tensile strength	85 N/cm	48 lbs/inch
Temperature Resistance:	-20°C to +155°C	Up to +311°F
Recommended curing cycle:	1 hour at 150°C or 2 hours at 130°C	
Electrical resistance through Adhesive*:	0.003 ohms	
RoHS compliant	Yes	
Storage Temperature	+12°C to +25°C	

Tested according to MIL STD 202G MIL STD 202F method 307 across Surface area of 1 sq. inch.

*Standard charge for certificate: £25.00.



NOTE

Except where indicated otherwise, the figures stated are typical values and should not be regarded as MAXIMUM or MINIMUM values for specification purposes. The Company reserves the right to improve products and any change in specification will result in a re-issue of the relevant 'Technical Data Sheet'. Customers should satisfy themselves that the tape is suitable for their requirements whether after such modifications or otherwise. Please check that you have the latest issue of the 'Technical Data Sheet'. All slitting and length tolerances are to British Standards. Before use the customer is advised to consult the Health & Safety Information Sheet produced by the company for this product, which is available on request.

STORAGE

Tapes stored below the minimum recommended temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.



AFERA

Association des Fabricants Européens de Rubans Auto-Adhésifs.

[Adding more to adhesive tape](#)

Registered in England No. 929843
Vat No. 115-6143-00

Advance Tapes International Limited
Westmoreland Avenue
Thurmaston
Leicester LE4 8PH
England

Tel. +44 (0)116 251 0191
Fax. +44 (0)116 265 2046
contact@advancetapes.com

www.advancetapes.com