TECHNICAL DATA

Version 10

AT66 PVC Protection Tape

General description

A PVC film coated with a low tack, cross – linked solvent based rubber – resin adhesive adhesive.

- Conformable to awkward shapes
- Water resistant
- Good abrasion resistance
- UV resistant
- Medium tack
- Good low temperature performance
- Easy tear
- Easy unwind
- Can be removed cleanly up to four weeks after application

0.13mm

- Low stretch
- Suitable for machine and hand application



Typical values

Thickness



Breaking Load 26 N/cm Elongation 140% Adhesion Steel 1.7 N/cm Self 1.7 N/cm Moisture Vapour Permeability 35-55g/m₂/24hrs Water Extract 6.0 to 7.0 pН Conductivity 1.0mS/m max. **RoHS** Compliant Yes Service Temperature -5°C to +60°C Application Temperature +5°C to +40°C Storage Temperature +12°C to +25°C

NOTE

Except where indicated otherwise, the figures stated are typical values and should not be regarded as MAXIMUM or MINIMUM values for specification purposes. The Company reserves the right to improve products and any change in specification will result in a re-issue of the relevant 'Technical Data Sheet'. Customers should satisfy themselves that the tape is suitable for their requirements whether after such modifications or otherwise. Please check that you have the latest issue of the 'Technical Data Sheet'. All slitting and length tolerances are to British Standards. Before use the customer is advised to consult the Health & Safety Information Sheet produced by the company for this product, which is available on request.

STORAGE

Tapes stored below the minimum recommended temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.



AFERA Association des Fabricants Européens de Rubans Auto-Adhésifs.

Adding more to adhesive tape

Registered in England No. 929843 Vat No. 115-6143-00 Advance Tapes International Limited Westmoreland Avenue Thurmaston Leicester LE4 8PH England Tel. +44 (0)116 251 0191 Fax. +44 (0)116 265 2046 contact@advancetapes.com

www.advancetapes.com