

# TECHNICAL DATA

Version 12

## AT68 Ribbed PVC Protection Tape

### General Description

A PVC film, ribbed for straight tear, coated with cross – linked solvent based rubber – resin adhesive.

- Conformable to awkward shapes
- Water resistant
- Good abrasion resistance
- UV resistant
- Medium tack
- Good low temperature performance
- Straight line easy tear
- Easy unwind
- Can be removed cleanly up to four weeks after application



### Technical Details

#### Typical Values

Thickness	0.15mm
Breaking Load	21 N/cm
Elongation	100%
Adhesion	
Steel	1.7 N/cm
Self	1.6 N/cm
RoHS Compliant	Yes
Service Temperature	-5°C to +60°C
Application Temperature	0°C to +40°C
Storage Temperature	+12°C to +25°C

#### NOTE

Except where indicated otherwise, the figures stated are typical values and should not be regarded as MAXIMUM or MINIMUM values for specification purposes. The Company reserves the right to improve products and any change in specification will result in a re-issue of the relevant 'Technical Data Sheet'. Customers should satisfy themselves that the tape is suitable for their requirements whether after such modifications or otherwise. Please check that you have the latest issue of the 'Technical Data Sheet'. All slitting and length tolerances are to British Standards. Before use the customer is advised to consult the Health & Safety Information Sheet produced by the company for this product, which is available on request.

#### STORAGE

Tapes stored below the minimum recommended temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.



#### AFERA

Association des Fabricants Européens de Rubans Auto-Adhésifs.

[Adding more to adhesive tape](#)

Registered in England No. 929843  
Vat No. 115-6143-00

Advance Tapes International Limited  
Westmoreland Avenue  
Thurmaston  
Leicester LE4 8PH  
England

Tel. +44 (0)116 251 0191  
Fax. +44 (0)116 265 2046  
[contact@advancetapes.com](mailto:contact@advancetapes.com)

[www.advancetapes.com](http://www.advancetapes.com)