

AT7 - PVC Electrical Insulation Tape

Features

- Flame retardant and self-extinguishing
- Easy unwind and tear
- W UV resistant
- Available in colour coding packs

Applications

- Colour coding & general protection and insulation of electrical components and wiring.
- · Cable management and bundling.
- Masking off during chemical and electro-plating.
- Cable harnessing, insulation, abrasion protection for OEM companies in household appliances market.

Adhesive type

Cross-linked solvent based rubber-resin

Technical

Thickness: 0.13 mm Breaking load: 26 N/cm Elongation: 180%

Adhesion to Steel: 2.4 N/cm Adhesion to Self: 2.1 N/cm Service Temp: -5°C to +70°C Breakdown voltage: 8kV RoHS Compliant: Yes

Specification

Conforms to BS EN 60454/Type 2

Standard colours



AT10 - PVC Heavy Duty Pipewrap Tape

Features

- Flame retardant and self-extinguishing
- Conformable
- Water and UV resistant
- Abrasion resistant

Applications

- Underground cable sealing system.
- Sealing and hooping of submerged energy cables.
- Corrosion and abrasion protection for pipework above or under ground.

Thickness: 0.25 mm
Breaking Load: 44 N/cm
Elongation: 220%
Adhesion to Steel: 3.3 N/cm
Adhesion to Self: 3.0 N/cm
Service Temperature: -5°C to +80°C

Breakdown Voltage: 10 kV RoHS Compliant: Yes

Specification

Technical

Conforms to BS EN 60454-3-1 Type 2



Standard colour

Adhesive type

Cross-linked solvent based rubber-resin

AT20 - PVC Extra Heavy Duty Pipewrap Tape

Features

- Flame retardant and self extinguishing
- Very high abrasion resistance
- UV & water resistant

Applications

- Corrosion and abrasion protection for pipework above or under ground
- Sealing and hooping of submerged energy cables
- Underground cable sealing system.

Technica

Thickness: 0.44 mm
Breaking load: 90 N/cm
Elongation: 200%
Adhesion to Steel: 3.0 N/cm
Adhesion to Self: 2.6 N/cm
Service Temp: +5°C to +80°C
Breakdown Voltage: 12 kV

Standard colour





Adhesive type

Cross - linked solvent based rubber - resin

AT79 - High Performance Polythene Self Amalgamating Tape

Features

Easy unwind

Conformable

Resistant to high and low temperatures

Water and UV resistant

Suitable for outdoor use

 Resistant to a wide range of chemicals including, alkalis, hydraulic fluids and vegetable oils

Technical

Thickness: 0.75 mm Breaking Load: 12 N/cm Elongation: 600%

Service Temperature: -35°C to +130°C Breakdown Voltage: 34 kV/mm RoHS Compliant: Yes



Applications

Insulation and waterproofing of electrical connections.

Standard colour



AT87 - Polyisobutylene Self Amalgamating Tape

Features

Easy unwind

Conformable

Resistant to high and low temperatures

Water and UV resistant

Ozone resistant

Resistant to a wide range of chemicals including, alkalis, hydraulic fluids and vegetable oils

Applications

- Insulation and waterproofing of electrical connections.
- · Sealing satellite dish cabling

Technical

Thickness: 0.5 mm
Breaking Load: 20 N/cm
Elongation: 600%
Service Temperature: -30°C to +100°C
Breakdown Voltage: 17 kV/mm
RoHS Compliant: Yes

Standard colour





AT4002 - Glass Cloth Tape Class F 155 °C

Features

High mechanical strength

High temperature resistance

Thermosetting adhesive

Conforms to BS EN 60454-3-8 Type 1

Applications

- Electrical insulation of coils.
- Insulation of square conductors in traction motors and generators.
- Tensional strapping of coils and armature windings.
- Termination building to protect the external layer of winding.

Adhesive type

Thermosetting solvent based rubber-resin

Technical

Thickness: 0.18 mm
Breaking Load: 280 N/cm
Elongation: 5%

Adhesion to Steel: 3.0 N/cm Breakdown Voltage: 2.5 kV RoHS Compliant: Yes

Specification

Recognised by UL. BS EN 60454-3-8 Type 2



Standard colour

Find out more information: www.advancetapes.com

DISTRIBUTED BY


Advance Tapes International Ltd Westmoreland Avenue Thurmaston LE4 8PH, England







Call: 00 44 (0)116 251 0191 Fax: 00 44 (0)116 265 2046 Email: sales@advancetapes.com





Disclaimer: Tape performance in multiple applications can be affected by various factors. These factors are often not within the control of Advance Tapes. Having better knowledge and control of individual applications and method of use, end users of the product are responsible for evaluating the suitability for a particular application and for identifying that the product is fit for the purpose. Customers should satisfy themselves that the tape is suitable for their requirements in a particular application prior to use.